

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
11 July 2002 (11.07.2002)

PCT

(10) International Publication Number
WO 02/053677 A1

(51) International Patent Classification⁷: **C09K 11/08**,
C09D 11/00, 5/22, B42D 15/00

(21) International Application Number: PCT/US01/49441

(22) International Filing Date:
21 December 2001 (21.12.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/755,407 5 January 2001 (05.01.2001) US

(71) Applicant (for all designated States except US):
BIOCRISTAL, LTD. [US/US]; 575 McCorkle Boul-
vard, Westerville, OH 43082-8888 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **BARBERA-
GUILLEM, Emilio** [US]; 1555 Picarde Court, Pow-
ell, OH 43065 (US).

(74) Agent: **CASEY, Sean, M.**; Sean M. Casey Co., L.P.A.,
P.O. Box 710, New Albany, OH 43054-0710 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN,
YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

WO 02/053677 A1

(54) Title: FLUORESCENT INK COMPOSITIONS COMPRISING FUNCTIONALIZED FLUORESCENT NANOCRYSTALS

(57) Abstract: A fluorescent ink composition comprising functionalized fluorescent nanocrystals, an aqueous-based ink carrier comprising water or a water-based solution, and a binder. Also provided are methods of providing an image or a security mark on a substrate for subsequent identification by applying a fluorescent ink composition onto the substrate.

**FLUORESCENT INK COMPOSITIONS COMPRISING FUNCTIONALIZED
FLUORESCENT NANOCRYSTALS**

5 Applicant: BIOCRYSTAL, LTD., Westerville, Ohio, U.S.A.

 Inventor:
 Emilio BARBERA-GUILLEM, Powell, Ohio, U.S.A.

10 This is an international patent application filed under the Patent Cooperation Treaty in
the United States Receiving Office that claims priority to U.S. Patent Appl. No. 09/755,407,
filed 05 JAN 01.

Field Of The Invention

15 This invention relates to water-based printing inks; and more particularly to
fluorescent ink compositions useful in various printing methods such as ink jet printing.

BACKGROUND OF THE INVENTION

 Ink jet printing is a standard and preferred method for printing onto a substrate,
20 wherein a stream of ink droplets are directed from a printing device to a surface of the
substrate. The direction of the stream is controlled electronically in causing the droplets to
print the desired image or information on the substrate surface without requiring contact
between the printing device and the surface to which the ink is applied. Ink jet printing may
be applied to a variety of substrates including, but not limited to, metals, glass, synthetic
25 resins, plastics, rubber, paper, and the like. Objects, comprising substrates to which ink jet
printing is well suited, include, but are not limited to, containers for consumer products,
currency, draft checks, envelopes, letterhead, identification cards, bank cards (debit, credit,
and the like), identification strips (e.g., comprising barcodes), and the like.

Fluorescent inks have been developed for printing a "security mark" on articles such that the mark is invisible to the unaided eye, but that can be detected as fluorescence upon excitation with an activating light of a suitable excitation wavelength spectrum. More particularly, security marks are applied to articles in efforts to prevent forgery, theft, and fraud; wherein such articles are known to include, but are not limited to, identification cards, passports, currency, checks, securities, and other types of commercial paper. The security mark may be in the form of a barcode which encodes information, or may comprise a recognizable pattern for identification and verification purposes. Prior art fluorescent inks are known in the art to include: a fluorescent colorant, a solvent, and a binder resin; an organic laser dye that is excited by a wavelength spectrum in the near infrared range and fluoresces in an infrared range; a phenoxazine derivative dye fluorescing in the near infrared range; a rare earth metal, an organic ink carrier, and may further comprise a chelating agent; and a near infrared fluorophore and a water-dissipatable polyester. Generally, such fluorescent inks comprising fluorescent dyes or pigments demonstrate several disadvantages.

For example, there is a relatively narrow margin between the amount of a fluorescent dye which is sufficient to give good fluorescent color intensity, and an amount wherein the dye molecules begin to aggregate and thus reduce the amount of fluorescence by quenching. A limitation in intensity can also limit the density of information encoded on a security mark (such as a barcode) by a fluorescent ink composition.

Thus, there exists a need for fluorescent ink compositions suitable for printing on substrates, wherein (a) the fluorescent component of the fluorescent ink composition is water-soluble; (b) the fluorescent component is excited by a wavelength spectrum comprising UV light, and preferably in a spectral range of from about 300 nanometers (nm) to about 400 nm, and emits an narrow emission peak in a wavelength spectrum primarily in the visible range,

and preferably in a spectral range of from about 410 nm to about 750 nm; (c) a plurality of fluorescent ink compositions (each containing a fluorescent component that can be detectably distinguished (e.g., by fluorescent color and/or intensity) from that of other fluorescent ink compositions of the plurality of fluorescent ink compositions) may be utilized for multicolor fluorescence by excitation with a single wavelength spectrum of light resulting in simultaneous detection of fluorescence of high quantum yield and with discrete peak emission spectra; (d) a fluorescent component that resists photobleaching (and therefore can be used for signal integration); and (e) a fluorescent component that is not susceptible to quenching.

SUMMARY OF THE INVENTION

Provided are fluorescent ink compositions comprising a fluorescent component that comprises functionalized fluorescent nanocrystals (e.g., a single type for print of a single fluorescent color, or a plurality of types for print of multicolor), an ink carrier, and a binder; and may further comprise other components such as one or more of a biocide, a surfactant, a defoamer, and the like. One or more fluorescent ink compositions are printed onto the surface of a substrate using a printer device. Following excitation of the printed surface with an appropriate excitation wavelength spectrum, each of the one or more fluorescent ink compositions printed on the surface will emit fluorescence of high quantum yield and with discrete peak emission. The fluorescent ink composition may be varied with respect to the intensity of fluorescence emission. Variables such as differences in intensity and in fluorescent color can enable an increase in the information that can be stored in a security mark, as well as increase the possible number of colors, intensity, and complexity of a security mark so as to prevent forgery. For example, the fluorescent ink composition can be

varied by controlling the amount and type of functionalized fluorescent nanocrystals in the method of preparing the fluorescent ink composition. Thus, the fluorescent properties of the fluorescent ink composition, such as intensity and color, are sensitive to the functionalized fluorescent nanocrystals made a part thereof. A resultant advantage of the fluorescent ink compositions of the present invention is that they may be produced to have a greater degree of fluorescence (intensity) than previously known fluorescent ink jet compositions.

An additional advantage of the use of the fluorescent ink compositions according to the present invention relates to the use of a plurality of the fluorescent ink compositions in printing a desired pattern onto a surface. Each fluorescent ink composition may be comprised of a type of functionalized fluorescent nanocrystals capable of fluorescing a specific color. Thus, the plurality of fluorescent ink compositions may be used to print a desired pattern which can be excited to emit multicolor fluorescence which may be visible simultaneously in generating a specific, identifiable code (based on the emission spectra which can comprise both color and intensity) that can be used for purposes of verification or identification. For example, a plurality of fluorescent ink compositions may comprise a first ink composition capable of fluorescing red, a second ink composition capable of fluorescing blue, a third ink composition capable of fluorescing yellow, and a fourth composition capable of fluorescing green. This exemplary combination of a fluorescent ink compositions may be used to print currency with a security mark comprising a code (based on the number, or number and intensity, of colors) for verification purposes. Further, in a method of producing the fluorescent ink composition according to the present invention, by controlling the proportion of the components, precise control may be achieved with respect to the basic fluorescent properties of the resultant fluorescent ink composition.

The above and other objects, features, and advantages of the present invention will be apparent with reference to the following Detailed Description of the Invention.

DETAILED DESCRIPTION OF THE INVENTION

5 Definitions

The term “functionalized fluorescent nanocrystals” is intended, for purposes of the specification and claims, to refer to nanocrystals comprising semiconductor nanocrystals or doped metal oxide nanocrystals, wherein the nanocrystals are operably bound to, and functionalized by the addition of, a plurality of molecules which provide the functionalized
10 fluorescent nanocrystals with reactive functionalities to enable the fluorescent nanocrystals to be soluble in the aqueous-based ink carrier of the fluorescent ink composition; wherein the plurality of molecules may be selected from the group consisting of carboxylic acid, an amino acid, a diaminocarboxylic acid, a monoaminocarboxylic acid, and a combination thereof. Further, the reactive functionalities may aid the functionalized nanocrystals to
15 become bound to one or more of the binder of the fluorescent ink composition, or the substrate onto which they are applied. A preferred type of molecules to functionalize the fluorescent nanocrystals may be used to the exclusion of molecules other than the preferred type of molecules. The functionalized nanocrystals are sufficiently soluble in an aqueous-based environment provided by an ink carrier in forming an aqueous-based fluorescent ink
20 composition.

The term “semiconductor nanocrystals” is intended, for purposes of the specification and claims, to refer to quantum dots (crystalline semiconductors) having a core comprised of at least one of a Group II-VI semiconductor material (of which ZnS, and CdSe are illustrative examples), or a Group III-V semiconductor material (of which GaAs is an illustrative

example), a Group IV semiconductor material, or a combination thereof. In a preferred embodiment, the core of the quantum dots may be passivated with an semiconductor overlayering ("shell") uniformly deposited thereon. For example, a Group II-VI semiconductor core may be passivated with a Group II-VI semiconductor shell (e.g., a ZnS or CdSe core may be passivated with a shell comprised of YZ wherein Y is Cd or Zn, and Z is S or Se). As known to those skilled in the art, the size of the semiconductor core correlates with the spectral range of emission. Table 1 is an illustrative example for CdSe.

Table 1

Color	Size Range(nm)	Peak Emission Range
blue	2.5 to 2.68	476 to 486
green	2.8 to 3.4	500 to 530
yellow	3.58 to 4.26	536 to 564
orange	4.9 to 6.1	590 to 620
red	8.6 to 10.2	644 to 654

In a preferred embodiment, the semiconductor nanocrystals are produced using a continuous flow process and system such as that disclosed in U.S. Patent No. 6,179,912, issued January 30, 2001 and entitled, "Continuous Flow Process for Production of Semiconductor Nanocrystals," and have a particle size that varies by less than +/- 4% in the average particle size. In a preferred embodiment, the semiconductor nanocrystals comprise a monodisperse population having an average particle size (as measure by diameter) in the range of approximately 1 nanometer (nm) to approximately 20 nm.

The term "doped metal oxide nanocrystals" is intended, for purposes of the specification and claims, to refer to nanocrystals comprised of: a metal oxide, and a dopant

comprised of one or more rare earth elements. For example, suitable metal oxides include, but are not limited to, yttrium oxide (Y_2O_3), zirconium oxide (ZrO_2), zinc oxide (ZnO), copper oxide (CuO or Cu_2O), gadolinium oxide (Gd_2O_3), praseodymium oxide (Pr_2O_3), lanthanum oxide (La_2O_3), and alloys thereof. The rare earth element comprises an element
5 selected from the Lanthanide series and includes, but is not limited to, europium (Eu), cerium (Ce), neodymium (Nd), samarium (Sm), terbium (Tb), gadolinium (Gd), holmium (Ho), thulium (Tm), an oxide thereof, and a combination thereof. As known to those skilled in the art, depending on the dopant, an energized doped metal oxide nanocrystal is capable of emitting light of a particular color. Thus, the nature of the rare earth or rare earths are
10 selected to obtain the color sought to be imparted (emitted) by a doped metal oxide nanocrystal used in the fluorescent ink composition according to the present invention. A given rare earth or rare earth combination has a given color, thereby permitting the provision of doped metal oxide nanocrystals, each of which may emit (with a narrow emission peak) a color over an entire range of colors by adjusting the nature of the dopant, the concentration of
15 the dopant, or a combination thereof. For example, the emission color and brightness (e.g., intensity) of a doped metal oxide nanocrystal comprising $Y_2O_3:Eu$ may depend on the concentration of Eu; e.g., emission color may shift from yellow to red with increasing Eu concentration. For purposes of illustration only, representative colors which may be provided are listed in Table 2.

Table 2

Fluorescent Color	Dopant
blue	thulium
blue	cerium
yellow-green	terbium
green	holmium
green	erbium
red	europium
reddish orange	samarium
orange	neodymium
yellow	dysprosium
white	praseodymium
orange-yellow	europium + terbium
orange-red	europium + samarium

Methods for making doped metal oxide nanocrystals are known to include, but are not limited
5 to, a sol-gel process (see, e.g., U.S. Patent No. 5,637,258), and an organometallic reaction.

As will be apparent to one skilled in the art, the dopant (e.g., one or more rare earth elements)
are incorporated into the doped metal oxide nanocrystal in a sufficient amount to permit the
doped metal oxide nanocrystal to be put to practical use in fluorescence detection as

described herein in more detail. An insufficient amount comprises either too little dopant

10 which would fail to emit sufficient detectable fluorescence, or too much dopant which would
cause reduced fluorescence due to concentration quenching. In a preferred embodiment, the

amount of dopant in a doped metal oxide nanocrystal is a molar amount in the doped metal oxide nanocrystal selected in the range of from about 0.1% to about 25%. Doped metal oxide nanocrystals may be excited with a single excitation light source resulting in a detectable fluorescence emission of high quantum yield (e.g., a single quantum dot having a

5 fluorescence intensity that may be a log or more greater than that of a molecule of a conventional fluorescent dye) and with a discrete fluorescence peak. Typically, they have a substantially uniform size of less than 200 Angstroms, and preferably have a substantially uniform size in the range of sizes of from about 1 nm to about 5 nm, or less than 1 nm. In a preferred embodiment, the doped metal oxide nanocrystals are comprised of metal oxides
10 doped with one or more rare earth elements, wherein the dopant comprising the rare earth element is capable of being excited (e.g., with ultra-violet light) to produce a narrow spectrum of fluorescence emission. In another preferred embodiment, the doped metal oxide has both fluorescent properties (when excited with an excitation light source) and magnetic properties. Thus, in one embodiment, a fluorescent ink composition may comprise
15 functionalized fluorescent nanocrystals comprising doped metal oxide nanocrystals which are magnetic.

The term "operably bound" is intended, for purposes of the specification and claims to refer to fusion or a bond or an association of sufficient stability to withstand conditions encountered in a method of detection, between a combination of different molecules such as,
20 but not limited to, between functionalized fluorescent nanocrystals and the binder, and between a fluorescent nanocrystal and the molecules with which it is functionalized (e.g., carboxylic acid, diaminocarboxylic acid, or a monoaminocarboxylic acid), and a combination thereof. As known to those skilled in the art, the bond may comprise one or more of covalent, ionic, hydrogen, van der Waals, and the like. As known to those skilled in the art,

and as will be more apparent with reference to the following embodiments, there are several methods and compositions in which two or more molecules may be operably bound utilizing reactive functionalities. Reactive functionalities include, but are not limited to, free chemical groups (e.g., thiol, or carboxyl, hydroxyl, amino, amine, sulfo, etc.), and reactive chemical groups (reactive with free chemical groups).

The term "suitable conditions" is used herein, for purposes of the specification and claims, and with reference to a process of reacting two components (e.g., functionalized fluorescent nanocrystals and a binder), to mean those conditions under which the components may become operably bound to each other. As known to those skilled in the art, such conditions may include one or more of: a pH range of from about 3 to about 9, ionic strengths such as that ranging from distilled water to about 1 molar sodium chloride, and a temperature in the range of from about 4°C to about 45°C; and may further include a time sufficient for binding to occur (e.g., in a range of from about 10 minutes to about 2 hours).

By the term "diaminocarboxylic acid" is intended, for purposes of the specification and claims, to refer to an amino acid that has two free amine groups. The amino acid may be a naturally occurring amino acid, a synthetic amino acid, a modified amino acid, an amino acid derivative, and an amino acid precursor (e.g., citrulline and ornithine are intermediates in the synthesis of arginine). In a preferred embodiment, the diaminocarboxylic acid contains neutral (uncharged) polar functional groups which can hydrogen bond with water, thereby making the diaminocarboxylic acid (and the quantum dot to which it is made a part of) relatively more soluble in aqueous solutions containing water than those with nonpolar functional groups. Exemplary diamino-carboxylic acids include, but are not limited to, lysine, asparagine, glutamine, arginine, citrulline, ornithine, 5-hydroxylysine, djenkolic acid, β -cyanoalanine, and synthetic diaminocarboxylic acids such as

3,4-diaminobenzoic acid, 2,3-diaminopropionic acid, 2,4-diaminobutyric acid, 2,5-diaminopentanoic acid, and 2,6-diaminopimelic acid.

The term "amino acid" is intended, for purposes of the specification and claims, to refer to a molecule that has at least one free amine group and at least one free carboxyl group.

- 5 The amino acid may have more than one free amine group, or more than one free carboxyl group, or may further comprise one or more free chemical reactive groups other than an amine or a carboxyl group (e.g., a hydroxyl, a sulfhydryl, a seleno group, etc.). The amino acid may be a naturally occurring amino acid, a synthetic amino acid, a modified amino acid, an amino acid derivative, and an amino acid precursor. The amino acid may further be
- 10 selected from the group consisting of a monoaminocarboxylic acid, and a diaminocarboxylic acid. In a preferred embodiment, the monoaminocarboxylic acid contains one or more neutral (uncharged) polar functional groups which can hydrogen bond with water, thereby making the monoaminocarboxylic acid (and the quantum dot to which it is made a part of) relatively more soluble in aqueous solutions containing water than those with non-polar
- 15 functional groups. Exemplary mono-aminocarboxylic acids include, but are not limited to, glycine, serine, threonine, cysteine, β -alanine, homoserine, γ -aminobutyric acid, and homocysteine. Other preferred amino acids include sulfur containing amino acids (e.g., cysteine, homocysteine, s-allyl-L-cysteine sulfoxide, taurine, penicillamine, and the like); and seleno containing amino acids (e.g., selenocysteine, selenohomocysteine, Se-
- 20 methylselenocysteine, selenocystine, selenohomocystine, and the like).

The term "carboxylic acid" is intended, for purposes of the specification and claims, to refer to a compound having the formula $\text{HS}(\text{CH}_2)_n\text{X}$, wherein X is a carboxylate (carboxylic moiety). And, "n" is a number in the range of from 1 to about 20, and preferably greater than 4. In a preferred embodiment, the thiol group of the carboxylic acid can be used

as a reactive functionality for the carboxylic acid to become operably bound to the nanocrystal, depending on the composition of the nanocrystal (e.g., to Cd, Zn and the like). Additionally, the carboxylic moiety of the carboxylic acid imparts water solubility to the nanocrystals. Exemplary carboxylic acids may include, but are not limited to, mercaptocarboxylic acid, or mercaptofunctionalized amines (e.g., aminoethanethiol-HCl, or 1-amino-2-methyl-2-propanethiol-HCl).

The present invention provides a fluorescent ink composition, suitable for printing a desired pattern on a substrate, comprising functionalized fluorescent nanocrystals, and an ink carrier. Also provided is a fluorescent ink composition comprising functionalized fluorescent nanocrystals, an ink carrier, and a binder. Also provided is a fluorescent ink composition comprising functionalized fluorescent nanocrystals, an ink carrier, a binder, and one or more additional components suitable for the function of an ink composition. In a preferred embodiment, the functionalized fluorescent nanocrystals are excitable by ultraviolet light, and fluoresce at a spectral wavelength having a peak emission in the range of from about 410 nm to about 900 nm. In a more preferred embodiment, the fluorescence is in the range of visible light.

FUNCTIONALIZED FLUORESCENT NANOCRYSTALS

As disclosed in detail in U.S. Patent No. 6,114,038, issued 5 SEP 00 and entitled,

“Functionalized Nanocrystals and Their Use in Detection Systems,” fluorescent nanocrystals comprise nanocrystals which have been functionalized by the addition of a plurality of molecules; and preferably, the molecules are selected from an amino acid, a carboxylic acid, and a combination thereof. For example, the nanocrystals may comprise semiconductor nanocrystals that have a core selected from the group consisting of CdSe,

CdS, and CdTe (collectively referred to as "CdX"), and may further comprise a characteristic shell comprised of YZ wherein Y is Cd or Zn, and Z is S, or Se. Typically, CdX core/YZ shell quantum dots are overcoated with trialkylphosphine oxide, with the alkyl groups most commonly used being butyl and octyl. In one preferred embodiment, the CdX core/YZ shell quantum dots are treated with a large excess of mercaptocarboxylic acid in exchanging the trialkylphosphine oxide coat with a coat comprising a plurality of carboxylic acid molecules. For example, (CdSe)ZnS nanocrystals were prepared in a pyridine solution. The pyridine overcoating of the (CdX) core/YZ shell nanocrystals were exchanged with a carboxylic acid comprising mercaptocarboxylic acid. Exchange of the coating group is accomplished by treating the water-insoluble, pyridine-capped quantum dots with a large excess of anhydrous mercaptocarboxylic acid. To accomplish this, the pyridine-capped (CdSe)ZnS quantum dots were precipitated with hexanes, and then isolated by centrifugation. The residue was dissolved in anhydrous mercaptoacetic acid, with a few drops of pyridine added, if necessary, to form a transparent solution. Chloroform was added to precipitate the nanocrystals and wash away excess thiol. The nanocrystals were isolated by centrifugation, washed once more with chloroform, and then washed with hexanes. The residue was briefly dried with a stream of argon. The resultant nanocrystals, coated with molecules of carboxylic acid, were then soluble in water or other aqueous solutions. The nanocrystals, in an aqueous solution, were centrifuged once more, filtered through a 0.2 μm filter, degassed with argon, and stored in an amber vial. The nanocrystals may then be further functionalized by an amino acid comprising a diaminocarboxylic acid. The diaminocarboxylic acid molecules were operably bound to the carboxylic acid molecules of the nanocrystals by using commercially available crosslinking agents and methods known to those skilled in the art. For example, the carboxylic acid-coated nanocrystals were dissolved in an aqueous buffer system (pH of about

7). To the nanocrystals was added EDC (1-ethyl-3-[3-dimethylaminopropyl] carbodi-imide) and sulfoNHS (sulfo-N-hydroxysuccinimide) in 500-1000 times excess. The resulting solution was stirred at room temperature for 30 minutes. Mercaptoethanol was added to neutralize unreacted EDC at 20 mM concentration and stirred for 15 minutes. The entire
5 solution was then added drop-wise, with stirring, to a solution of a diaminocarboxylic acid comprising lysine (large excess) in the same buffer; and the mixture was stirred for 2 hours at room temperature. Ethanolamine (30 mM) was added to quench the reaction; and the mixture was stirred for 30 minutes at room temperature or left overnight at 4°C. The solution was centrifuged to remove any precipitated solids, and then ultrafiltered through a 30kD MW
10 centrifugal filter. The resultant concentrated, fluorescent nanocrystals can be solubilized in an aqueous solution of choice. Once solubilized, the resulting solution can be stored in an amber vial under an inert gas to prevent flocculation. The fluorescent nanocrystals may be operably bound to a successive layer of amino acid molecules by, for example, repeating the procedure and reaction using EDC and sulfoNHS with the amino acid molecules comprising
15 the successive layer.

Similarly, a nanocrystal comprising a doped metal oxide nanocrystal may be operably bound to a plurality of molecules (e.g., a carboxylic acid, an amino acid, or a combination thereof) using methods known in the art. For example, the plurality of molecules having reactive functionalities comprising free carboxyl groups can be chemisorbed, adsorbed, or
20 otherwise permanently added to the metal oxide portion of the nanocrystal. For example, the metal oxide nanocrystals are suspended in an aqueous solution of an amino acid comprising homocysteine having a pH of about 3.5 for about an hour. The reaction is then stopped by adjusting the pH to neutral, and dialyzing out the aqueous solution.

As an alternative, fluorescent nanocrystals functionalized with a plurality of a sulfur containing amino acid or a seleno containing amino acid. In a preferred embodiment, the fluorescent nanocrystals were functionalized with homocysteine molecules. Nanocrystals (e.g., (CdSe)ZnS) coated with an organic layer (e.g., mercaptoacetic acid) were treated with a molar excess of homocysteine in replacing the organic layer with a coating comprising a plurality of homocysteine molecules. The approximate number of surface Zn sites on the specific size of nanocrystals utilized was calculated. At least a 5 times molar excess of homocysteine (as compared to the number of surface Zn sites) was added to the nanocrystals, as per the following formula:

$$\text{Grams homocysteine} = 5(\text{number of Zn surface sites})(\text{volume of solution containing the nanocrystals})(\text{concentration of nanocrystals in solution})(135.2).$$

The mixture was stirred to dissolve the homocysteine, and then stored at 4°C for 24 hours.

The resultant solution was then centrifuged to remove any precipitate, and the supernatant was transferred to a centrifugal filter for the appropriate volume of supernatant (preferably, with a molecular weight cutoff of about 10 kD or below to retain the fluorescent nanocrystals coated with homocysteine). After centrifugation, and when the desired minimum volume is reached, the fluorescent nanocrystals were then rediluted in the appropriate aqueous solution (e.g., HEPES buffer) to a volume in which the original mass of homocysteine had been dissolved. The steps of filtering and redilution of the fluorescent nanocrystals in solution may be repeated to improve purity. The resultant fluorescent nanocrystals comprising homocysteine-coated nanocrystals may then be degassed by bubbling with an inert gas, and then stored at 4°C in an amber bottle.

The functionalized fluorescent nanocrystals used in the fluorescent ink composition according to the present invention are (a) functionalized to be water soluble and to enhance stability in water or a water-based solution; (b) a class of nanocrystals that may be excited with a single excitation light source resulting in detectable fluorescence emissions of high quantum yield and with discrete fluorescence peaks; (c) functionalized so as to have reactive functionalities, such as may be used to operably bind to a binder, if desired; and (d) resistant to photobleaching and fading. "Water-soluble" is used herein to mean sufficiently soluble or dispersible in water or water-based solutions. Preferably, the functionalized fluorescent nanocrystals used in a fluorescent ink composition comprise a substantially uniform size of less than 100 Angstroms, and preferably have a substantially uniform size in the range of from about 2 nm to about 10 nm (diameter). As apparent to one skilled in the art, the amount of the functionalized fluorescent nanocrystals contained within the fluorescent ink composition according to the present invention will depend on factors such as the desired intensity of the emitted fluorescence, the nature of the fluorescent nanocrystals comprising the functionalized fluorescent nanocrystals, the desired viscosity of the fluorescent ink composition, the nature of the substrate onto which is printed the fluorescent ink composition, and the nature of the printer device (e.g., ink jet printer) for which the fluorescent ink composition is intended. In a preferred embodiment, the amount of functionalized fluorescent nanocrystals is in the range of from about 0.0005% to about 5%, based on the total weight of the fluorescent ink composition.

INK CARRIER

Any suitable aqueous-based ink carrier may be used to prepare the fluorescent ink composition according to the present invention. Suitable aqueous-based ink carriers should

provide sufficient solubility for the various components of the fluorescent ink composition (e.g., functionalized fluorescent nanocrystals and binder). A suitable aqueous-based ink carrier comprises water (preferably deionized water), or a mixture of water and at least one water-soluble organic solvent. As apparent to one skilled in the art, the selection of the ink carrier will depend on factors such as the desired drying time of the fluorescent ink composition, the desired surface tension and viscosity of the fluorescent ink composition, the nature of the substrate onto which is printed the fluorescent ink composition, and the nature of the printer device (e.g., ink jet printer) for which the fluorescent ink composition is intended. Similarly, depending on such factors, the amount of the ink carrier in the fluorescent ink composition according to the present invention may vary. In a preferred embodiment, the amount of ink carrier is in the range of from about 75% to about 99.5%, based on the total weight of the fluorescent ink composition.

In the case of an aqueous-based ink carrier comprising a mixture of water and at least one water-soluble organic solvent, the amount of water is sufficient for solubilization of the functionalized fluorescent nanocrystals therein. In a preferred embodiment, the aqueous-based ink carrier contains from about 40% to about 95% water (based on total weight of the aqueous-based ink carrier), and more preferably, from about 60% to about 95% water; with the balance being the one or more water-soluble organic solvents. It is further preferred that the water-soluble organic solvent not adversely affect the peak fluorescent emission wavelength or the intensity of the fluorescent emission of excited functionalized fluorescent nanocrystals in the fluorescent ink composition. Water-soluble solvents are known to those skilled in the art to include, but are not limited to, citrus solvents (e.g., citrus peel oils, terpine, terpinene, dipentene, and the like), a polyhydric alcohol (e.g., ethylene glycol, propylene glycol, butylene glycol, triethylene glycol, thiodiglycol, diethylene glycol,

hexylene glycol, and the like), an alcohol (e.g., methanol, ethanol, propanol, butanol), a polyalkyl glycol (e.g., polyethylene glycol), alkyl ethers of a polyhydric alcohol, ketones or ketoalcohols, sulfur containing compounds (e.g., dimethyl sulfoxide, tetramethyl sulfone), and esters (e.g., ethylene carbonate, propylene carbonate).

5

BINDER

The fluorescent ink composition may optionally comprise a binder. The binder serves to immobilize, or increase the adhesion of, the fluorescent ink composition to the substrate on which it is printed. The binder is soluble or dispersible in the ink carrier of the fluorescent ink composition, and preferably should not adversely affect the peak fluorescent emission wavelength or the intensity of the fluorescent emission of excited functionalized fluorescent nanocrystals in the fluorescent ink composition. A water-soluble or water-dispersible binder is known to those skilled in the art to include, but is not limited to, one or more of: an acrylic polymer, starch, a polyvinyl alcohol, glycerol, polyethylene glycol, carboxymethylcellulose, hydroxyethyl cellulose, polysodium acrylate, polysodium methacrylate, styrene-acrylic copolymers, styrene-maleic copolymers, pectinic acid, and the like. As apparent to one skilled in the art, the selection and amount of the binder will depend on factors such as the desired surface tension and viscosity of the fluorescent ink composition, the desired water dispersibility, the nature of the substrate onto which is printed the fluorescent ink composition, and the nature of the printer device (e.g., ink jet printer) for which the fluorescent ink composition is intended. In a preferred embodiment, the amount of binder is in the range of from about 1% to about 25%, based on the total weight of the fluorescent ink composition. In a preferred embodiment in which the fluorescent ink composition is used in an ink jet printer, a suitable amount of binder is added to the fluorescent ink composition so

as to comprise a viscosity suitable for ink jet printing; i.e., within the range of from about 1 to 20 centipoises (cps), and more preferably, 1.5 to 8 cps.

In a most preferred embodiment, each molecule of binder comprises one or more reactive functionalities that is reactive with (e.g., can be used to operably bind to) one or more reactive functionalities of functionalized fluorescent nanocrystals in forming the fluorescent ink composition according to the present invention. Operably binding the binder to the functionalized fluorescent nanocrystals can result in production of a durable cross-linked fluorescent ink composition that may improve adhesion and surface tension of the fluorescent ink composition to the surface of the substrate onto which it is printed; as well as improving the stability of the fluorescent ink composition in storage and/or printing operation conditions. For example, a molecule of binder comprises one or more free chemical groups, and the functionalized fluorescent nanocrystals each comprise multiple molecules of reactive functionality comprising reactive chemical groups which are capable of becoming operably bound (e.g., ionically) to the reactive functionalities of the binder under suitable conditions so that a fluorescent ink composition is formed to have functionalized fluorescent nanocrystals cross-linked with binder. In continuing with an illustrative example, a molecule of binder comprises reactive functionalities comprising amino groups, and the functionalized fluorescent nanocrystals comprise reactive functionalities comprising amino-reactive groups (e.g., carboxyl or amine). In another illustrative example, the binder comprises reactive functionalities comprising carboxyl groups and the functionalized fluorescent nanocrystals comprise reactive functionalities comprising carboxyl-reactive groups (e.g., amine). Binders having at least one free carboxyl group may include, but are not limited to, carboxylated cellulose derivatives (e.g., carboxyethyl cellulose, carboxypropyl cellulose, carboxymethyl cellulose, hydroxylalkyl celluloses, alkyl celluloses, hydroxypropyl methylcellulose), alginic

acid, pectinic acid, esterified starches, polymeric carboxylic acids (e.g., polyacrylic acids, polymethacrylic acids, polymaleic acids), polymeric sulfonic acids, and polycarboxylated vinyl polymers. A preferred binder comprises carboxymethyl cellulose. Binders having at least one amine group may include, but are not limited to, polyethylene glycol end-capped with amine, caseinate, soybean protein, gelatin, polyvinyl amines, polyallyl amines, amine-functionalized lignin, amine-functionalized acrylic resins (e.g., dimethyl amino ethyl methacrylate), and amine-functionalized cellulose derivatives (e.g., aminoethyl-cellulose, aminopropylcellulose). The binder of the fluorescent ink composition according to the present invention may comprise one type or a plurality of types of binders.

In a preferred embodiment, the functionalized fluorescent nanocrystals, ink carrier, and binder comprise at least about 90% by weight of the fluorescent ink composition.

ADDITIONAL COMPONENTS

The fluorescent ink composition may comprise an additional component selected from the group consisting of a biocide, a defoamer, a surfactant, a corrosion inhibitor, and a combination thereof. Surfactants may be added to improve the wettability of the fluorescent ink composition to the surface of the substrate onto which it is printed. Surfactants may include, but are not limited to, ethoxylated tetramethyl decynediol, alkylbenzene sulfonates, alkyl-naphthyl sulfonates, alcohol sulfates, perfluorinated carboxylic acids, alkylesters of polyethylene glycol, fatty acid esters of glycol, alkylamines, amphoteric surfactants, and a combination thereof. In a preferred embodiment in which the fluorescent ink composition comprises a surfactant as a component, the surfactant may be present in the fluorescent ink composition in an amount of from about 0.01% to about 1.5% by weight of the fluorescent ink composition. A defoamer prevents foaming of the fluorescent ink composition during its

preparation, as well as during the printing operation. Any suitable defoamer known to those skilled in the art may be used as an additional component in the fluorescent ink composition according to the present invention; and more preferably, the defoamer is soluble or dispersible in the ink carrier of the fluorescent ink composition. A defoamer may comprise one or more of a mixture of tetramethyldecynediol and propylene glycol, a silicone defoamer, an acetylenic defoamer, and the like. In a preferred embodiment in which the fluorescent ink composition comprises a defoamer as a component, the defoamer may be present in the fluorescent ink composition in an amount of from about 0.5% to about 1.2% by weight of the fluorescent ink composition. A biocide is one or more agents to prevent growth of bacteria, mold, or fungus in the fluorescent ink composition. Any suitable biocide known to those skilled in the art may be used as an additional component in the fluorescent ink composition according to the present invention; and more preferably, the biocide is soluble or dispersible in the ink carrier of the fluorescent ink composition. A suitable biocide may include, but is not limited to, one or more of benzoate salts, sorbate salts, methyl p-hydroxybenzoate, 6-acetoxy-2,2-dimethyl-1,3-dioxane, 1,2-benzisothiazolin-3-one, and the like. In a preferred embodiment in which the fluorescent ink composition comprises a biocide as a component, the biocide may be present in the fluorescent ink composition in an amount of from about 0.02% to about 0.5% by weight of the fluorescent ink composition. A corrosion inhibitor may be added to the fluorescent ink composition to inhibit or reduce corrosion, such as of the metal parts of the printer device (e.g., nozzles or orifices). Any suitable corrosion inhibitor known to those skilled in the art may be used as an additional component in the fluorescent ink composition according to the present invention; and more preferably, the corrosion inhibitor is soluble or dispersible in the ink carrier of the fluorescent ink composition. A suitable corrosion inhibitor may include, but is not limited to, one or more of the 1H-

benzotriazoles. In a preferred embodiment in which the fluorescent ink composition comprises a corrosion inhibitor as a component, the corrosion inhibitor may be present in the fluorescent ink composition in an amount of from about 0.01% to about 0.5% by weight of the fluorescent ink composition.

5

METHOD OF MANUFACTURE

As appreciated by those skilled in the art of inks, the fluorescent ink compositions according to the present invention may be prepared in any number of ways. However, a preferred method of formulating the fluorescent ink compositions comprises mixing the functionalized fluorescent nanocrystals into the aqueous-based ink carrier comprising water or a water-based solution, and then added to and mixed therein is a binder. For fluorescent ink compositions that further comprise one or more additional components (e.g., surfactant, biocide, corrosion inhibitor), the one or more additional components may then be added to and mixed in the fluorescent ink composition. The final mixture may be stirred until a blended, consistent composition is obtained. The fluorescent ink composition may be filtered, if desired, e.g., to remove any impurities.

10
15

PRINTING DEVICES

As apparent to one skilled in the art of printing, the printing device utilized will depend on the printing method in which the fluorescent ink compositions according to the present invention are applied. In one embodiment, each of a plurality of the fluorescent ink compositions is placed in a separate well of a printing device containing multiple wells for holding ink or ink cartridges, in loading the printing device with fluorescent ink compositions that may be used in combination to print an image (e.g., security mark or one or more

20

patterns) that is capable of fluorescing in multiple colors when exposed to a single excitation light source suitable for exciting the functionalized fluorescent nanocrystals of the fluorescent ink compositions. The fluorescent inks are printed onto a substrate by the printing device in ratios appropriate to yield the desired colors and to form the desired image. In a preferred
5 embodiment, the printing device is an ink jet printer.

PRINTING METHODS

The fluorescent ink compositions according to the present invention may be used in many printing methods such as ink jet printing, screen printing, gravure printing, letterpress
10 printing, offset printing, relief printing, intaglio printing, and the like. As apparent to one skilled in the art, the viscosity of the fluorescent ink compositions will vary depending on the printing method, the printer device, and the substrate onto which the fluorescent ink compositions are printed. For example, a preferred viscosity for ink jet printing may range from about 1.5 to about 15 cps; and more preferably, from about 3 to about 6 cps. In
15 contrast, a preferred viscosity for screen printing may range from about 100 to about 400 cps; and more preferably, from about 200 to about 300 cps. Printed images, generated using the printing method and fluorescent ink compositions according to the present invention, are fluorescent when exposed to an excitation light source (e.g., UV light); and thus become visible or detectable as a color (or colors when more than one fluorescent ink composition is
20 used in the printing method) in the range of from about 410 nm to about 900 nm.

SUBSTRATES

The fluorescent ink compositions according to the present invention may be used to print on a number of suitable substrates which may include, but are not limited to,

conventional papers (computer paper, currency paper, bond paper, copying paper, image paper), glass, rubber, vinyl, plastics, fabrics, films, inorganic substrates (e.g., metals and woods), and the like. In a preferred embodiment, the substrate comprises a porous or absorbent substrate, such as paper.

5

METHODS FOR IDENTIFICATION OF AN OBJECT

As apparent to those skilled in the art from the descriptions herein, one or more of the fluorescent ink compositions of the present invention may be used in a method of providing an object with a security marking for purposes of identification (which may further encompass verification). In one embodiment, a method for identifying an object comprising the steps of:

10

(a) applying a security mark to the object using a fluorescent ink composition comprising functionalized fluorescent nanocrystals, an aqueous-based ink carrier comprising water or a water-based solution, and a binder;

15

(b) exposing the object to an excitation light source having a wavelength spectrum in a range of from about 300 nm to about 400 nm;

(c) visualizing the security mark by detecting a peak fluorescent emission in a spectral range of from about 410 nm to about 750 nm; and

(d) identifying the object in response to visualizing the security mark.

20

In another embodiment, a plurality of fluorescent ink compositions are used to apply a security mark to the object, wherein each of the plurality of fluorescent ink compositions is capable of fluorescing a specific (e.g., different than that emitted by any other of the fluorescent ink compositions in the plurality of fluorescent ink compositions) color in

providing a security mark which fluoresces in multicolor when visualized; and identification is based on the visualization of the security mark fluorescing in multicolor.

As appreciated by those skilled in the art, the exact components, the proportion of the components, and properties of the components, desired for an ink composition will depend on the application, printing method, and substrate. Therefore, routine experimentation may be required to determine the components and the proportion of the components which are optimum in forming a fluorescent ink composition for a given application and with the desired properties.

The following examples are provided to further illustrate the present invention, and are not to be construed as limiting the invention in any manner.

Example 1

For purposes of illustration, listed in Table 3 are various examples of a fluorescent ink composition according to the present invention, wherein the fluorescent ink composition comprised functionalized fluorescent nanocrystals, and an ink carrier. The components are listed by their weight percent of the composition; wherein the functionalized fluorescent nanocrystals (e.g., homocysteine-coated fluorescent nanocrystals) are abbreviated as "FNC"; and the ink carrier ("IC") comprised water (H₂O) and at least one water soluble organic solvent ("WSO"). The water soluble organic solvents used for purposes of illustration included dimethyl sulfoxide ("DMSO") and polyethylene glycol ("PEG"). The resultant fluorescent ink compositions were printed on a white plain paper substrate (a stock of standard copy paper lacking substantial background fluorescence), and allowed to dry. The print was invisible to the unaided eye. The paper substrate was then exposed to UV light, and

the print appeared the appropriate color due to the fluorescence of the fluorescent ink composition used.

Table 3

FNC	IC
<1%	H ₂ O > 94%; DMSO 5%
<1%	H ₂ O > 59%; DMSO 40%
<1%	H ₂ O > 94%; PEG 5%
<1%	H ₂ O > 59%; PEG 40%

5

Example 2

For purposes of illustration, listed in Table 4 are various examples of a fluorescent ink composition according to the present invention, wherein the fluorescent ink composition comprised functionalized fluorescent nanocrystals ("FNC"), an ink carrier ("IC"), and a binder. The resultant fluorescent ink compositions were printed on a white plain paper substrate (a stock of standard copy paper lacking substantial background fluorescence), and allowed to dry. The print was invisible to the unaided eye. The paper substrate was then exposed to UV light, and the print appeared the appropriate color due to the fluorescence of the fluorescent ink composition used.

10

Table 4

FNC	IC	Binder
<1%	H ₂ O > 34%; PEG 40%	glycerol 25%
<1%	H ₂ O > 58%; DMSO 40%	glycerol 1%
<1%	H ₂ O > 58%; PEG 40%	glycerol 1%
<1%	H ₂ O > 93%; DMSO 5%	starch 1%
<1%	H ₂ O > 93%; DMSO 5%	gelatin 1%
<1%	H ₂ O > 58%; DMSO 40%	gelatin 1%

Example 3

For purposes of illustration, listed in Table 5 are various examples of a fluorescent ink composition according to the present invention, wherein the fluorescent ink composition comprised functionalized fluorescent nanocrystals, an ink carrier ("IC"), a binder, and a surfactant. For each composition illustrated in Table 5, functionalized fluorescent nanocrystals were in a weight percent of less than 1%. Illustrative surfactants included triethylamine ("TEA"), and detergent (TRITON; "TTN"). The resultant fluorescent ink compositions were printed on a white plain paper substrate (a stock of standard copy paper lacking substantial background fluorescence), and allowed to dry. The print was invisible to the unaided eye. The paper substrate was then exposed to UV light, and the print appeared the appropriate color due to the fluorescence of the fluorescent ink composition used.

Table 5

IC	Binder	Surfactant
H ₂ O > 92%; DMSO 5%	gelatin 1%	0.01% TEA
H ₂ O > 92%; DMSO 5%	gelatin 1%	0.1% TEA
H ₂ O > 92%; DMSO 5%	gelatin 1%	1% TEA
H ₂ O > 88%; DMSO 5%	gelatin 5%	0.01% TEA
H ₂ O > 88%; DMSO 5%	gelatin 5%	0.1% TEA
H ₂ O > 88%; DMSO 5%	gelatin 5%	1% TEA
H ₂ O > 92%; DMSO 5%	gelatin 1%	0.01% TTN
H ₂ O > 92%; DMSO 5%	gelatin 1%	0.1% TTN
H ₂ O > 92%; DMSO 5%	gelatin 1%	1% TTN
H ₂ O > 88%; DMSO 5%	gelatin 5%	0.01% TTN
H ₂ O > 88%; DMSO 5%	gelatin 5%	0.1% TTN
H ₂ O > 92%; PEG 5%	gelatin 1%	1% TEA
H ₂ O > 92%; PEG 5%	gelatin 1%	1% TTN

The foregoing description of the specific embodiments of the present invention have been described in detail for purposes of illustration. In view of the descriptions and illustrations, others skilled in the art can, by applying current knowledge, readily modify and/or adapt the present invention for various applications without departing from the basic concept, and therefore such modifications and/or adaptations are intended to be within the meaning and scope of the appended claims.

WHAT IS CLAIMED IS:

1. A fluorescent ink composition comprising functionalized fluorescent nanocrystals, an aqueous-based ink carrier comprising water or a water-based solution, and a binder.
- 5 2. The fluorescent ink composition according to claim 1, further comprising an additional component selected from the group consisting of a biocide, a surfactant, a defoamer, a corrosion inhibitor, and a combination thereof.
3. The fluorescent ink composition according to claim 1, wherein the functionalized
10 fluorescent nanocrystals comprise semiconductor nanocrystals.
4. The fluorescent ink composition according to claim 1, wherein the functionalized fluorescent nanocrystals comprise doped metal oxide nanocrystals.
- 15 5. The fluorescent ink composition according to claim 1, wherein the functionalized fluorescent nanocrystals are excitable by exposure to a wavelength spectrum in a spectral range of from about 300 nm to about 400 nm, and fluoresces at a peak emission wavelength in the spectral range of from about 410 nm to about 750 nm.
- 20 6. The fluorescent ink composition according to claim 1, wherein the functionalized fluorescent nanocrystals comprise fluorescent nanocrystals functionalized by a plurality of molecules comprising amino acid.

7. The fluorescent ink composition according to claim 1, wherein the functionalized fluorescent nanocrystals comprise a substantially uniform size in the range of about 2 nm to about 10 nm.

5 8. The fluorescent ink composition according to claim 1, wherein the functionalized fluorescent nanocrystals comprise an amount in the range of from about 0.0005% to about 5%, based on total weight of the fluorescent ink composition.

9. The fluorescent ink composition according to claim 1, wherein the aqueous-based ink
10 carrier comprises water.

10. The fluorescent ink composition according to claim 1, wherein the aqueous-based ink carrier comprises a water-based solution comprising a mixture of water and at least one water-soluble organic solvent.

15 11. The fluorescent ink composition according to claim 1, wherein the aqueous-based ink carrier comprises an amount in the range of from about 75% to about 99.5%, based on total weight of the fluorescent ink composition.

20 12. The fluorescent ink composition according to claim 1, wherein the binder comprises an amount in the range of from about 1% to about 25%, based on total weight of the fluorescent ink composition.

13. The fluorescent ink composition according to claim 1, wherein the functionalized fluorescent nanocrystals are operably bound to the binder in forming a cross-linked fluorescent ink composition.

14. The fluorescent ink composition according to claim 2, wherein the functionalized fluorescent nanocrystals and the aqueous-based ink carrier and the binder comprise at least 90% by weight of the fluorescent ink composition.

15. The fluorescent ink composition according to claim 2, wherein the fluorescent ink composition further comprises a defoamer in the range of from about 0.5% to about 1.2% by weight of the fluorescent ink composition.

16. The fluorescent ink composition according to claim 2, wherein the fluorescent ink composition further comprises a surfactant in the range of from about 0.01% to about 1.5% by weight of the fluorescent ink composition.

17. The fluorescent ink composition according to claim 2, wherein the fluorescent ink composition further comprises a biocide in the range of from about 0.02% to about 0.5% by weight of the fluorescent ink composition.

18. The fluorescent ink composition according to claim 2, wherein the fluorescent ink composition further comprises a corrosion inhibitor in the range of from about 0.01% to about 0.5% by weight of the fluorescent ink composition.

19. A method of formulating the fluorescent ink composition according to claim 1, wherein the method comprises: contacting the functionalized fluorescent nanocrystals with the aqueous-based ink carrier in forming a mixture; and adding a binder to the mixture in forming the fluorescent ink composition.

5

20. A method of providing an image on a substrate for subsequent identification comprising applying onto the substrate a fluorescent ink composition comprising functionalized fluorescent nanocrystals, an aqueous-based ink carrier comprising water or a water-based solution, and a binder.

10

21. A method according to claim 20, wherein the image comprises a security mark.

22. A method according to claim 20, wherein the fluorescent ink composition further comprises an additional component selected from the group consisting of a biocide, a surfactant, a defoamer, a corrosion inhibitor, and a combination thereof.

15

23. A method according to claim 20, further comprising applying onto the substrate a plurality of fluorescent ink compositions wherein each of the plurality of fluorescent ink compositions is capable of fluorescing a specific color in providing an image which is multicolor upon subsequent identification.

20

24. The method according to claim 20, wherein the functionalized fluorescent nanocrystals are operably bound to the binder in forming a cross-linked fluorescent ink composition.

25. An image formed by the method according to claim 20.
26. An image comprising a security mark formed by the method according to claim 21.
- 5 27. An image formed by the method according to claim 22.
28. An image formed by the method according to claim 23.
- 10 29. An image formed by the method according to claim 24.
30. A substrate having printed thereon an image according to claim 25.
31. A substrate having printed thereon an image according to claim 26.
- 15 32. A substrate having printed thereon an image according to claim 27.
33. A substrate having printed thereon an image according to claim 28.
- 20 30. A substrate having printed thereon an image according to claim 29.
33. A method for identifying an object comprising the steps of:

(a) applying a security mark to the object using a fluorescent ink composition comprising functionalized fluorescent nanocrystals, an aqueous-based ink carrier comprising water or a water-based solution, and a binder;

5 (b) exposing the object to an excitation light source having a wavelength spectrum in a range of from about 300 nm to about 400 nm;

(c) visualizing the security mark by detecting a peak fluorescent emission in a spectral range of from about 410 nm to about 750 nm; and

(d) identifying the object in response to visualizing the security mark.

10 34. The method according to claim 33, further comprising applying a security mark to the object using a plurality of fluorescent ink compositions, wherein each of the plurality of fluorescent ink compositions is capable of fluorescing a specific color in providing a security mark which fluoresces in multicolor when visualized; and identifying the object based on the visualization of the security mark fluorescing in multicolor.

15

35. The method according to claim 33, wherein the fluorescent ink composition further comprises an additional component selected from the group consisting of a biocide, a surfactant, a defoamer, a corrosion inhibitor, and a combination thereof.

20 36. The method according to claim 33, wherein the functionalized fluorescent nanocrystals are operably bound to the binder in forming a cross-linked fluorescent ink composition.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US01/49441

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : C09K 11/08; C09D 11/00, 5/22; B42D 15/00

US CL : 252/301.36; 106/31.15, 31.32, 31.64; 283/92; 428/690

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 252/301.36; 106/31.15, 31.32, 31.64; 283/92; 428/690

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A,E	US 2002/0021003 A1 (McGREW) 21 February 2002, whole doc.	1-36
A,P	US 6,251,303 B1 (BAWENDI et al) 26 June 2001, whole. doc.	1-36
A	US 6,114,038 A (CASTRO et al) 05 September 2000, whole doc.	1-36
A	US 5,990,197 A (ESCANO et al) 23 November 1999, whole doc.	1-36
A	US 5,733,971 A (FELDMANN-KRANE et al) 31 March 1998, whole doc.	1-36
A	US 5,837,042 A (LENT et al) 17 November 1998, whole doc.	1-36

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

"	Special categories of cited documents:	"T"	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A"	document defining the general state of the art which is not considered to be of particular relevance	"X"	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E"	earlier document published on or after the international filing date	"Y"	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L"	document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"A"	document member of the same patent family
"O"	document referring to an oral disclosure, use, exhibition or other means		
"P"	document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

07 MAY 2002

Date of mailing of the international search report

28 MAY 2002

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

C. MELISSA KOSLOW

Telephone No. (703) 308-0661

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US01/49441

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5,623,001A (FIGOV) 22 April 1997, whole doc.	1-36